TRANSLATION PATENT COOPERATION TREATY PCT

INTERNATIONAL PRELIMINARY REPORT ON PATENTABILITY

(Chapter II of the Patent Cooperation Treaty)

(PCT Article 36 and Rule 70)

Applicant's or agent's file reference RX03P21USPCT		FOR FURTHER A	ACTION	See Form PCT/IPEA/416
International application No.		International filing d	ate (day/month/year)	Priority date (day/month/year)
				23.03.2004
1	International Patent Classification (IPC) or national classification and IPC H01F10/14, H01F1/053			
Applicant JAPAN	Applicant JAPAN SCIENCE AND TECHNOLOGY AGENCY			
l. Th	 This report is the international preliminary examination report, established by this International Preliminary Examining Authority under Article 35 and transmitted to the applicant according to Article 36. 			
2. Th	is REPORT consists of a to	otal of 3	sheets, including	this cover sheet.
3. Th	is report is also accompani	ed by ANNEXES, comprising	:	
a.	(sent to the applic	cant and to the International B	ureau) a total of 2	sheets, as follows:
	sheets of the description, claims and/or drawings which have been amended and are the basis for this report and/or sheets containing rectifications authorized by this Authority (see Rule 70.16 and Section 607 of the Administrative Instructions).			
	sheets which supersede earlier sheets, but which this Authority considers contain an amendment that goes beyond the disclosure in the international application as filed, as indicated in item 4 of Box No. I and the Supplemental Box.			
b.		national Bureau only) a total of	(indicate type and number	r of electronic carrier(s))
				, containing a sequence listing and/or tables
	related thereto, in computer readable form only, as indicated in the Supplemental Box Relating to Sequence Listing (see Section 802 of the Administrative Instructions).			
4. Th	is report contains indication	ons relating to the following ite	ms:	
	Box No. I Bas	sis of the report		
	Box No. II Pric	ority		
	Box No. III No	n-establishment of opinion wit	regard to novelty, inventive step and industrial applicability	
Box No. IV Lack of unity of invention				
	Box No. V Reasoned statement under Article 35(2) with regard to novelty, inventive step or industrial applicability; citations and explanations supporting such statement			tty, inventive step or industrial applicability;
Box No. VI Certain documents cited				
	Box No. VII Cer	tain defects in the internationa	l application	
L	Box No. VIII Certain observations on the international application			
Date of sub	mission of the demand		Date of completion of th	is report
Name and mailing address of the IPEA/JP		Authorized officer		
Enceimile N			Telephone No	

INTERNATIONAL PRELIMINARY REPORT ON PATENTABILITY

International application No.

PCT/JP2005/005183

Box	No. I	Basis of the report		
1.		regard to the language, this report is based on the internation ated under this item.	nal application in the language in w	hich it was filed, unless otherwise
		This report is based on translations from the original language		
		which is the language of a translation furnished for the purposition of the purposition o	oses of:	
		international search (Rule 12.3 and 23.1(b)) publication of the international application (Rule 12.4)		
		international preliminary examination (Rule 55.2 and/		
2.	With	regard to the elements of the international application, this	report is based on (replacement sh	eets which have been furnished to the
	recei	ving Office in response to an invitation under Article 14 are eport):	e referred to in this report as "ori	ginally filed" and are not annexed to
		the international application as originally filed/furnished		
	\boxtimes	the description:		
		pages 1-2,4-14		as originally filed/furnished
		pages* 3	received by this Authority on _	20.01.2006
		pages*	received by this Authority on _	
	\boxtimes	the claims:		
		nos. 2		as originally filed/furnished
		nos.*	as amended (together	with any statement) under Article 19
		nos.* 1,4		
		nos.*		
	∇		, _	
		the drawings:		as originally filed/furnished
		sheets Fig. 1-6	received by this Authority on	
		a sequence listing and/or any related table(s) - see Supplem	ental Box Relating to Sequence Lis	sung.
3.	\boxtimes	The amendments have resulted in the cancellation of:		
		the description, pages		
		the claims, nos. 3		
		the drawings, sheets/figs		
		the sequence listing (specify):		
		any table(s) related to sequence listing (specify):		
4.		This report has been established as if (some of) the amend they have been considered to go beyond the disclosure as fi	led, as indicated in the Supplement	al Box (Rule 70.2(c)).
		the description, pages		
		the claims, nos.		
		the drawings, sheets/figs		
		the sequence listing (specify):		
		any table(s) related to sequence listing (specify):		
*	If ite	m 4 applies, some or all of those sheets may be marked "sup	erseded."	

INTERNATIONAL PRELIMINARY REPORT ON PATENTABILITY

International application No.
PCT/JP2005/005183

Box No. V Reasoned statement under Article 35(2) with regard to novelty, inventive step or industrial applicability; citations and explanations supporting such statement			
1.	Statement		
	Novelty (N) Claims 1, 2, 4	_ YES	
	Claims	_ NO	
	Inventive step (IS) Claims	_ YES	
	Claims 1, 2, 4		
	Industrial applicability (IA) Claims 1, 2, 4	YES	
	Claims		
2.	Citations and explanations (Rule 70.7)		
2.	Document 1: JP 2002-164238 A (Hitachi Metals, Ltd.), 7		
	June 2002, claims; paragraphs [0012], [0016]		
	and [0025] to [0029] & US 2002/54824 A1		
	Document 2: JP 7-283016 A (TDK Corporation), 27 October		
	1995, claims; paragraphs [0005], [0026],		
	[0027] and [0050] to [0058]		
	Document 3: JP 7-201623 A (TDK Corporation), 4 August		
	1995, paragraphs [0036] to [0044], [0050] to		
	[0053], [0065] to [0067] and [0082] & US		
	5641363 A1 & US 5834663 A1		
	Document 4: JP 2003-158006 A (Shin-Etsu Chemical Co.,		
	Ltd.), 30 May 2003, [claim 1]; paragraphs		
	[0009] to [0013] & EP 1455368 A1 & WO		
	2003/044810 A1		
	Document 5: JP 2003-64454 A (Shin-Etsu Chemical Co.,		
	Ltd.), 5 March 2003, paragraphs [0009] to		
	[0016] & US 2003/79805 A1 & EP 1267365 A2		
	Document 6: JP 9-45567 A (Hitachi Metals, Ltd.), 14		
	February 1997, paragraph [0008] & US 5876518		
	A1 & US 6254694 B1		
	Document 7: JP 7-272929 A (Kobe Steel, Ltd.), 20 October		
	1995, paragraphs [0006], [0009], [0010] and		
	[0016]		
l			

INTERNATIONAL PRELIMINARY REPORT ON PATENTABILITY

International application No.
PCT/JP2005/005183

Box No. V

Reasoned statement under Article 35(2) with regard to novelty, inventive step or industrial applicability; citations and explanations supporting such statement

Claim 1

It would be easy for a person skilled in the art to combine the feature pertaining to a magnet set forth in documents 1 to 6 with the feature pertaining to a thin-film magnet set forth in document 7 to constitute the invention set forth in claim 1 of this application.

Claim 2

It would be easy for a person skilled in the art to conceive of combining the feature pertaining to a magnet set forth in documents 1 to 3 with the feature pertaining to a thin-film magnet set forth in document 7 to constitute the invention set forth in claim 2 of this application.

Claim 4

Documents 1 to 5 set forth the method for preparing a magnet set forth in claim 4 of this application.

特許協力条約

PCT

特許性に関する国際予備報告(特許協力条約第二章)

(法第12条、法施行規則第56条) (PCT36条及びPCT規則70)

出願人又は代理人 の書類記号 RX03P21USPCT	今後の手続きについては、様式PCT/IPEA/416を参照すること。		
国際出願番号 PCT/JP2005/005183	国際出願日 (日. 月. 年) 23. 03. 2005	優先日 (日.月.年) 23.03.2004	
国際特許分類(I P C) Int.Cl. H01F10/14	1 (2006.01) i, H01F1/053 (2006.01) i		
出願人 (氏名又は名称) 独立行政法人科学技術振興機構			
■ 補正されて、この報告の基本 囲及び/又は図面の用紙()	規定に従い送付する。 と含めて全部で <u>3</u> ペ れている。 ページである。 礎とされた及び/又はこの国際予備審 PCT規則 70.16 及び実施細則第 607 년	ージからなる。 査機関が認めた訂正を含む明細書、請求の範	
国際予備審査機関が認定した b. 電子媒体は全部で 配列表に関する補充欄に示す。	た差替え用紙	(電子媒体の種類、数を示す)。	
b. 電子媒体は全部で 配列表に関する補充欄に示す。 (実施細則第802号参照)	た差替え用紙 ように、電子形式による配列表又は配	(電子媒体の種類、数を示す)。	
b. 電子媒体は全部で 配列表に関する補充欄に示す。 (実施細則第 802 号参照) 4. この国際予備審査報告は、次の内容を 第 I 欄 国際予備審査報 第 II 欄 優先権 第 第 II 欄 新規性、進歩性 第 第 IV 欄 発明の単一性の	た差替え用紙 ように、電子形式による配列表又は配金 を含む。 吸告の基礎 生又は産業上の利用可能性についての国 つ欠如 に規定する新規性、進歩性又は産業上の 状及び説明 て献	(電子媒体の種類、数を示す)。 列表に関連するテーブルを含む。	
b. 電子媒体は全部で配列表に関する補充欄に示す。(実施細則第802号参照) 4. この国際予備審査報告は、次の内容を第1欄 国際予備審査執 第11欄 優先権 第11例 発明の単一性の第1V欄 発明の単一性の第V欄 PCT35条(2) けるための文献 第VI欄 ある種の引用文 第VI欄 国際出願の不偏 第四欄 国際出願に対す	た差替え用紙 ように、電子形式による配列表又は配金 を含む。 吸告の基礎 生又は産業上の利用可能性についての国 つ欠如 に規定する新規性、進歩性又は産業上の 状及び説明 て献	(電子媒体の種類、数を示す)。 列表に関連するテーブルを含む。 国際予備審査報告の不作成 の利用可能性についての見解、それを裏付	
b. 電子媒体は全部で配列表に関する補充欄に示す。 (実施細則第802号参照) 4. この国際予備審査報告は、次の内容を第1欄 国際予備審査報 第11欄 優先権 第11欄 発明の単一性の 第V欄 PCT35条(2) けるための文献 第VI欄 国際出願の不偏	た差替え用紙 ように、電子形式による配列表又は配え を含む。 限告の基礎 主又は産業上の利用可能性についての国 の欠如 に規定する新規性、進歩性又は産業上の 状及び説明 て献 情 する意見	(電子媒体の種類、数を示す)。 列表に関連するテーブルを含む。 国際予備審査報告の不作成 の利用可能性についての見解、それを裏付	

東京都千代田区霞が関三丁目4番3号

第	[欄	報告の基礎 			
1.	1. 言語に関し、この予備審査報告は以下のものを基礎とした。				
	7	出願時の言語による国際出願			
	*****	出願時の言語から次の目的のための言語である			
	•				
		国際公開(PCT規則12.4(a))			
		国際予備審査 (PCT規則55.2(a)又は55.3(a))			
2.	このた差	報告は下記の出願書類を基礎とした。(法第6条(PCT14条)の規定に基づく命令に応答するために提出され 替え用紙は、この報告において「出願時」とし、この報告に添付していない。)			
		出願時の国際出願書類			
	V	明細書			
		第 1-2, 4-14 ページ、出願時に提出されたもの			
		第3ページ*、20.01.2006付けで国際予備審査機関が受理したもの第付けで国際予備審査機関が受理したもの			
	5.7	請求の範囲			
	\$ * 7.3	第 2 項、出願時に提出されたもの			
		第 項*、PCT19条の規定に基づき補正されたもの			
		第 1 , 4 項*、2 0 . 0 1 . 2 0 0 6 付けで国際予備審査機関が受理したもの			
		第 項*、 付けで国際予備審査機関が受理したもの			
	V	図面			
	3.7	第 $1-6$			
		第 ページ/図*、 付けで国際予備審査機関が受理したもの			
		第 ページ/図*、 付けで国際予備審査機関が受理したもの 第 ページ/図*、 付けで国際予備審査機関が受理したもの			
	** **:	配列表又は関連するテーブル			
	₹:	配列表に関する補充欄を参照すること。			
3.	V	補正により、下記の書類が削除された。			
		明細書 第請求の範囲 第3項			
		図面 第 <u> </u>			
		配列表 (具体的に記載すること)			
		配列表に関連するテーブル(具体的に記載すること)			
	,	切出い、 45-1			
4.	1:	この報告は、補充欄に示したように、この報告に添付されかつ以下に示した補正が出願時における開示の範囲を超えてされたものと認められるので、その補正がされなかったものとして作成した。 (PCT規則70.2(c))			
		第ページ			
		明細書 第 ページ 請求の範囲 第 項 図面 第 ページ/図			
		9WV			
		(1) 配列表(具体的に記載すること) ・・・・・・・・・・・・・・・・・・・・・・・・・・・・・・・・・・・・			
* 4	4. ∤	に該当する場合、その用紙に "superseded" と記入されることがある。			

第V欄 新規性、進歩性又は産業上の利用可能性についての法第 12 条 (PCT35 条(2)) に定める見解、 それを裏付ける文献及び説明				
1. 見解				
新規性(N)	請求の範囲 <u>1,2,4</u> 請求の範囲	有 無		
進歩性(IS)	請求の範囲	有 無		
産業上の利用可能性(IA)	請求の範囲 <u>1,2,4</u> 請求の範囲	有 無		
2. 文献及び説明 (PCT規則 7	70. 7)			
	38 A(日立金属株式会社)2002.06.07,特許請求の範囲、段落【0016】、段落【0025】-【0029】	I、段落 & US		
段落【000	A(ティーディーケイ株式会社)1995.10.27,特許請求の 5】、段落【0026】-【0027】、段落【0050】	か範囲、 - 【 O		
-【0044 067】、段落	A(ティーディーケイ株式会社)1995.08.04, 段落【0 】、段落【0050】-【0053】、段落【0065】 客【0082】 & US 5641363 A1 & US 5834663 A1	- [0		
落【0009 文献5:JP 2003-6445 【0016	006 A (信越化学工業株式会社) 2003.05.30, 【請求項: 】-【0013】 & EP 1455368 A1 & WO 2003/044810 64 A (信越化学工業株式会社) 2003.03.05, 段落【00 】 & US 2003/79805 A1 & EP 1267365 A2	A1 O 9]		
文献 6:JP 9-45567 A(I A1 & US 62540	日立金属株式会社) 1997. 02. 14,段落【O O O 8】 & US 5	5876518		
文献 7 : JP 7-272929 A	A(株式会社神戸製鋼所)1995.10.20,段落【0006】 -【0010】、段落【0016】	、段落		
	れた磁石に関する事項を、文献 7 に記載された薄膜磁石 請求の範囲 1 に係る発明とすることは、当業者の容易に			
	れた磁石に関する事項を、文献7に記載された薄膜磁石 請求の範囲2に係る発明とすることは、当業者の容易に			
請求の範囲4 文献1-5には、請	求の範囲4に記載された磁石の製造方法が記載されてレ	いる。		

研究を鋭意重ねた結果、焼結磁石と同様の核発生型保磁力機構を有する薄膜磁石 を製作することに成功した。

- [0012] すなわち、本発明は、(1)膜厚が 0.2~400 µ m であり、物理的に基材上に成膜された28~45質量%のR元素(但し、Rは希土類ランタニド元素の一種又は二種以上)を含むR-F e-B系合金において、結晶粒径が0.5~30 µ mのR₂Fe₁₄B結晶と、該結晶の境界にR元素が富化した粒界相との複合組織を有することを特徴とするR-Fe-B系海膜磁石、である。
- [0013] また、本発明は、(2)R₂Fe₁₄B結晶の磁化容易軸であるC軸が無配向であるか、あるいは膜面に対して略垂直に配向していることを特徴とする、上記(1)のR-Fe-B系 薄膜磁石、である。

[0014]

- [0015] さらに、本発明は、(4)R-Fe-B系合金の物理的成膜中又は/及びその後の熱処理において、700~1200℃に加熱することによって結晶粒成長とR元素が富化した粒界相の形成を行うことを特徴とする、上記(1)または(2)のR-Fe-B系薄膜磁石の製造方法、である。
- [0016] Nd-Fe-B系薄膜磁石の結晶組織がほとんどR₂Fe₁₄B結晶で構成され、且つその 結晶粒径が0.3μmに相当する単磁区粒子径未満である場合には、磁界を加えて も各結晶粒の磁化方向は磁界の大きさに対して徐々に回転するため、図1(b)の従 来例の薄膜磁石の初磁化曲線に見られる通り充分な着磁をすることが困難である。 また、薄膜磁石は微小なデバイスに応用する例が多いために、微小な部位に大きな 磁界を加えることが実際面で難しい。
- [0017] 一方、結晶組織が単磁区粒径より大きいR₂Fe₁₄B結晶と、該結晶境界にR元素が 富化した粒界相との複合組織から成る本発明磁石の場合に、磁界を加えると、後述 する図3の本発明試料(2)の初磁化曲線から推測されるように、各結晶粒内に存在 する多数の磁区が、隣接する磁壁を取り払って小さな磁界で一斉に磁界の方向を向 き、焼結磁石に類似した充分な着磁が行われる。この着磁性の困難さと容易さにつ いては、従来例の薄膜磁石が単磁区粒子型の保磁力発生機構を有し、一方、本発 明による薄膜磁石が核発生型の保磁力発生機構を有するためと推察される。

請求の範囲

- [1] (補正後) 膜厚が 0.2~400 μm であり、物理的に基材上に成膜された 28~45 質量%の R元素 (但し、Rは希土類ランタニド元素の一種又は二種以上)を含むRーFeーB系合 金において、結晶粒径が 0.5~30 μmのR₂Fe₁₄B結晶と、該結晶の境界にR元素 が富化した粒界相との複合組織を有することを特徴とするR-Fc-B系薄膜砕石。
- [2] R_2 Fe_{14} B結晶の磁化容易軸であるC軸が無配向であるか、あるいは膜面に対して略垂 直に配向していることを特徴とする、請求項1記載のR-Fe-B 系薄膜破石。
- [3] (削除)
- [4] (補正後) R-Fe-B系合金の物理的成膜中又は/及びその後の熱処理において、700 ~1200℃に加熱することによって結晶粒成長とR元素が富化した粒界相の形成を行う ことを特徴とする、請求項1または2に記載のR-Fe-B系薄膜磁石の製造方法。